



Gadres 3050

Fast "Shrink Free Resin." Ideal for Point repairs as there is Zero annular gap after curing. Gives typically a generous 20 minutes working time above ground and cures near instantly below ground within minutes after that. No more Waiting for Resins to Cure

[Click on Picture to View Video](#)




Ambient cure	Yes
Range of Pot Life at 70 deg F	15- 30 mins
Range of Time to Hardness at 42 deg F	40 - 80 mins
Range of Time to Hardness at 70 deg F	25-35 mins
Range of Time to Hardness at 125 deg F	< 10 mins
Supply style	Resin and accelerator premixed , hardener sold with kit
Shrinkage over 1%	No
Smell	Low styrene smell
Supply Size	40 x 3kg

Physical Properties in Liquid State

Colour:	Straw
Specific Gravity :	1.18
Viscosity:	800-1200 cps
Shelf life:	3 months
Acid value(mgKOH/g)	8
Solids content:	52
Flashpoint:	31 degrees C

Physical Properties of resin in polyester felt liner:

Temperature of deflection under load:	72
Hardness (GYZJ 934-1):	48
Water Absorption (mg):	15
Flexural strength (Mpa):	37 MPa
Flexural modulus (Mpa):	2300 MPa
Elongation at break (%):	1.50%



GADMON INDUSTRIES

Gadmon Industries,
57 Glengall Road, London SE 15 6NF,
United Kingdom,
Tel: +44 207 277 8878,
Fax: +44 207 277 9476
Email: sales@gadmon.com
Web: www.gadmon.com
Distribution Worldwide from UK, US and
Germany