



Gadres 4000

"Summer Resin". Give maximum working time of up to 5 hours yet cures quickly below ground with or without assistance of heat. Ideal for long shots or work in Summer.

[Click on Picture to View Video](#)



Ambient cure	Yes
Range of Pot Life at 70 deg F	2-3 hrs
Range of Time to Hardness at 42 deg F	4 - 6 hrs
Range of Time to Hardness at 70 deg F	3-6 hrs
Range of Time to Hardness at 125 deg F	< 1 hrs
Supply style	Resin and accelerator premixed , sold with hardener
Shrinkage over 1%	Yes
Smell	Average styrene smell
Supply Size	20 x 20kg

Physical Properties in Liquid State

Colour:	Straw
Specific Gravity :	1.18
Viscosity:	800-1200 cps
Shelf life:	3 months
Acid value(mgKOH/g)	8
Solids content:	52
Flashpoint:	31 degrees C

Physical Properties of resin in polyester felt liner:

Temperature of deflection under load:	72
Hardness (GYZJ 934-1):	48
Water Absorption (mg):	15
Flexural strength (Mpa):	37 MPa
Flexural modulus (Mpa):	2300 MPa
Elongation at break (%):	1.50%



**GADMON
INDUSTRIES**

Gadmon Industries,
57 Glengall Road, London SE 15 6NF,
United Kingdom,
Tel: +44 207 277 8878,
Fax: +44 207 277 9476
Email: sales@gadmon.com
Web: www.gadmon.com
Distribution Worldwide from UK, US and
Germany