

## Gadres 6000 Mix Tables

Gadres 6000 in Litres per feet			Gadres 6000 Mix 120 per feet			Gadres 6000 Mix 180 per feet		
Diameter (inches)	Thickness (mm)	Total Qty of resin in Ltr per feet	Gadres 6000 (ltr)	Gadcat 40 (ml)	Gadcell 10 (ml)	Gadres 6000 (ltr)	Gadcat 40 (ml)	Gadcell 10 (ml)
4	3.0	0.37	0.35	16.46	0.00	0.35	12.80	12.80
5	3.0	0.46	0.44	20.58	0.00	0.44	16.01	16.01
6	3.0	0.55	0.52	24.70	0.00	0.53	19.21	19.21
6	4.5	0.82	0.79	37.04	0.00	0.79	28.81	28.81
8	4.5	1.10	1.05	49.39	0.00	1.06	38.41	38.41
8	6.0	1.46	1.40	65.85	0.00	1.41	51.22	51.22
10	6.0	1.83	1.75	82.32	0.00	1.77	64.02	64.02
12	6.0	2.20	2.10	98.78	0.00	2.12	76.83	76.83
12	7.5	2.74	2.62	123.48	0.00	2.65	96.04	96.04
15	6.0	2.74	2.62	123.48	0.00	2.65	96.04	96.04
15	7.5	3.43	3.28	154.34	0.00	3.31	120.05	120.05
16	6.0	2.93	2.80	131.71	0.00	2.82	102.44	102.44
16	7.5	3.66	3.49	164.63	0.00	3.53	128.05	128.05
18	7.5	4.12	3.93	185.21	0.00	3.97	144.05	144.05
18	9.0	4.94	4.72	222.26	0.00	4.77	172.87	172.87
20	7.5	4.57	4.37	205.79	0.00	4.41	160.06	160.06
20	9.0	5.49	5.24	246.95	0.00	5.30	192.07	192.07
24	7.5	5.49	5.24	246.95	0.00	5.30	192.07	192.07
24	9.0	6.59	6.29	296.34	0.00	6.35	230.49	230.49
24	12.0	8.78	8.39	395.12	0.00	8.47	307.32	307.32

Gadres 6000 in Litres per metre			Gadres 6000 Mix 120 per m			Gadres 6000 Mix 180 per m		
Diameter (inches)	Thickness (mm)	Total Qty of resin in Ltr per metre	Gadres 6000 (ltr)	Gadcat 40 (ml)	Gadcell 10 (ml)	Gadres 6000 (ltr)	Gadcat 40 (ml)	Gadcell 10 (ml)
4	3.0	1.20	1.15	54.00	0.00	1.16	42.00	42.00
5	3.0	1.50	1.43	67.50	0.00	1.45	52.50	52.50
6	3.0	1.80	1.72	81.00	0.00	1.74	63.00	63.00
6	4.5	2.70	2.58	121.50	0.00	2.61	94.50	94.50
8	4.5	3.60	3.44	162.00	0.00	3.47	126.00	126.00
8	6.0	4.80	4.58	216.00	0.00	4.63	168.00	168.00
10	6.0	6.00	5.73	270.00	0.00	5.79	210.00	210.00
12	6.0	7.20	6.88	324.00	0.00	6.95	252.00	252.00
12	7.5	9.00	8.60	405.00	0.00	8.69	315.00	315.00
15	6.0	9.00	8.60	405.00	0.00	8.69	315.00	315.00
15	7.5	11.25	10.74	506.25	0.00	10.86	393.75	393.75
16	6.0	9.60	9.17	432.00	0.00	9.26	336.00	336.00
16	7.5	12.00	11.46	540.00	0.00	11.58	420.00	420.00
18	7.5	13.50	12.89	607.50	0.00	13.03	472.50	472.50
18	9.0	16.20	15.47	729.00	0.00	15.63	567.00	567.00
20	7.5	15.00	14.33	675.00	0.00	14.48	525.00	525.00
20	9.0	18.00	17.19	810.00	0.00	17.37	630.00	630.00
24	7.5	18.00	17.19	810.00	0.00	17.37	630.00	630.00
24	9.0	21.60	20.63	972.00	0.00	20.84	756.00	756.00
24	12.0	28.80	27.50	1296.00	0.00	27.79	1008.00	1008.00

**NOTE** The information provided in these tables is based on results from laboratory tests in a dark temperature controlled chamber. The users is strongly advised to carry out tests to verify the applicability to each particular situation prior to use, as factors such as wind chill, UV light, humidity WILL affect the results.

## Gadres 6000 Mix Tables (cont'd)

Gadres 6000 in lbs per feet		Gadres 6000 Mix 120 per feet			Gadres 6000 Mix 180 per feet		
Diameter (inches)	Thickness (mm)	Gadres 6000 (lbs)	Gadcat 40 (lbs)	Gadcell 10 (lbs)	Gadres 6000 (lbs)	Gadcat 40 (lbs)	Gadcell 10 (lbs)
4	3.0	0.85	0.04	0.00	0.85	0.03	0.03
5	3.0	1.06	0.05	0.00	1.07	0.04	0.04
6	3.0	1.27	0.06	0.00	1.28	0.05	0.04
6	4.5	1.90	0.09	0.00	1.92	0.07	0.06
8	4.5	2.54	0.12	0.00	2.56	0.09	0.08
8	6.0	3.38	0.16	0.00	3.42	0.12	0.11
10	6.0	4.23	0.20	0.00	4.27	0.15	0.14
12	6.0	5.07	0.24	0.00	5.13	0.19	0.17
12	7.5	6.34	0.30	0.00	6.41	0.23	0.21
15	6.0	6.34	0.30	0.00	6.41	0.23	0.21
15	7.5	7.93	0.37	0.00	8.01	0.29	0.26
16	6.0	6.76	0.32	0.00	6.84	0.25	0.23
16	7.5	8.46	0.40	0.00	8.54	0.31	0.28
18	7.5	9.51	0.45	0.00	9.61	0.35	0.32
18	9.0	11.41	0.54	0.00	11.53	0.42	0.38
20	7.5	10.57	0.50	0.00	10.68	0.39	0.35
20	9.0	12.68	0.60	0.00	12.82	0.46	0.42
24	7.5	12.68	0.60	0.00	12.82	0.46	0.42
24	9.0	15.22	0.72	0.00	15.38	0.56	0.51
24	12.0	20.29	0.96	0.00	20.51	0.74	0.68

**NOTE** The information provided in these tables is based on results from laboratory tests in a dark temperature controlled chamber. The users is strongly advised to carry out tests to verify the applicability to each particular situation prior to use, as factors such as wind chill, UV light, humidity WILL affect the results.